



TECHNICAL DATA

RESIN PACK 7A

Product Description

Resin Pack 7A is a two-component polyurethane foam specifically formulated for the sealing of telecommunications cable ducting against the ingress of moisture and gas.

Features

- * Fully complies with BT Specification M225.
- * Supplied as two half litre cans containing the base and hardener components.
- * Kit also contains an injection syringe.

Typical Uncured Physical Properties

Property	Base	Hardener
Viscosity (mPas)	1100-2000	250
Colour	Clear water white	Brown
Specific Gravity	1.05	1.23
Mix Ratio (by weight)	32	37
(by volume)	1	1

Note: The above technical information and data should be considered representative or typical only and should not be used for specification purposes.



RESULTS OF RESIN PACK 7A TESTED AGAINST BT SPECIFICATION M225

CLAUSE	TEST	SPEC REQUIREMENT	RESULTS
4.2.1.	Cream Time	Between 30 and 70 seconds	60 seconds
4.2.2.	Compressive Strength	≥ 0.3 MPa	0.42 MPa
4.2.3.	Volume Increase	Volume of resin to be between 10 and 15 times the total volume of uncured components	Increase is 11-12 times total volume
4.2.4.	Cure	To be set to a cured state within 5 hours @ 20°C and 24 hours @ 5°C	Material cures within set limits
4.2.5.	Effect on Cable Sheath	No adverse effect on polyethylene	No adverse effect on polyethylene
4.2.6.	Apparent Density	60-100 kg/m ³	67 kg/m ³
4.2.7.	Performance Test	Seal to withstand a 3 m head of water for 24 hours without leakage	Seal will withstand a 3 m head of water without leakage



ALH Group



Directions for use

Pour equal volumes of each component into syringe and stir rapidly for 30 seconds. Then follow application instructions.

Surface Preparation

Cables and joints should be prepared as per instructions.

Storage and Shelf Life

18 months at 5-25°C.



Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. All Products should be used in accordance with your own COSHH Assessments. For additional health and safety information, call 01373 858234.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that ALH believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond ALH's control and uniquely within user's knowledge and control can affect the use and performance of an ALH product in a particular application. Given the variety of factors that can affect the use and performance of an ALH product, the user is solely responsible for evaluating the ALH product and determining whether it is fit for a particular purpose and suitable for the user's methods of application.

Warranty, Limited Remedy and Disclaimer

Unless an additional warranty is specifically state on the applicable ALH product packaging or product literature, ALH warrants that each ALH product meets the applicable ALH product specification at the time ALH ships the product. ALH MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the ALH product does not conform to this warranty, then the sole and exclusive remedy is, at ALH's option, replacement of the ALH product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, ALH will not be liable for any loss or damage arising from the ALH product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.