



TECHNICAL DATA

NP1436

CLEAR ELECTRICAL EPOXY RESIN SYSTEM

Water Resistant

Product Description

NP1436 is a two-component unfilled epoxy resin system. The resin forms an excellent transparent, water resistant barrier around encapsulated components. The resin is flexible and adhesive, protecting components subjected to thermal fluctuations.

The LED Range of Resins

The NP1436 two-component clear epoxy from our LED range of resins has been developed for difficult environmental conditions. The system is slightly flexible (Shore D 55) and cures with a relatively low exothermic temperature rise (for an epoxy) with a 40-50-minute gel. It does have a slight colour but this does not significantly yellow with weathering. The very low water uptake has meant that NP1436 is a system of choice for LED indicators in marine and chemical environments.

Features

- * Clear
- * Slightly Flexible
- * Excellent Electrical properties
- * Water Resistant

Typical Uncured Physical Properties

Property	Base	Hardener	Mixed System
Viscosity (mPas)	2500	4000	
Colour	Clear	Clear Straw	Clear Straw
Specific Gravity	1.16	0.94	
Mix Ratio	100 100	80 100	By Weight By Volume



Pot Life	15 Minutes	100 g @ 23°C
Gel Time	40-50 Minutes	100 g @ 23°C
Full Cure	7 Days	100 g @ 23°C
Peak Exotherm	+115	°C / 100 g
Time to Peak Exotherm	50	Minutes / 100 g

Typical Cured Properties

Property	Result	Units
Operating Temperature	-40 to +125	°C Continuous
Shore D Hardness	55	After 72 hours
Electric Strength	15	kV/mm
Continuous Tracking Index	>850	V
Thermal Conductivity	0.2	W/mK
Deflection Temperature	30	°C (Approx)
Water Absorption	0.2	% (30 days @ 20 °C)

Note: The above technical information and data should be considered representative or typical only and should not be used for specification purposes.

Supply	Details
Twinpacks	Ideal for mixing without the entrapment of air.
Kits	The resin base and hardener are supplied in two separate containers, pre-weighed to facilitate accurate mixing for larger applications.
Bulk	Available in proportioned containers.
Shelf Life	The materials should be stored in the original unopened containers under cool dry conditions at temperatures between 10 and 25°C. The shelf life is two years. Opened containers should be resealed.



Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. All Products should be used in accordance with your own COSHH Assessments. For additional health and safety information, call 01373 858234.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that ALH believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond ALH's control and uniquely within user's knowledge and control can affect the use and performance of an ALH product in a particular application. Given the variety of factors that can affect the use and performance of an ALH product, the user is solely responsible for evaluating the ALH product and determining whether it is fit for a particular purpose and suitable for the user's methods of application.

Warranty, Limited Remedy and Disclaimer

Unless an additional warranty is specifically state on the applicable ALH product packaging or product literature, ALH warrants that each ALH product meets the applicable ALH product specification at the time ALH ships the product. ALH MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the ALH product does not conform to this warranty, then the sole and exclusive remedy is, at ALH's option, replacement of the ALH product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, ALH will not be liable for any loss or damage arising from the ALH product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Version: 2
Date: August 2019